



ENSOFT SD-141-85A

ENSOFT-S

Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is medium mineral filled, completely recyclable and suitable for general purpose applications. ENSOFT® series can be processed with conventional thermoplastics machinery
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Excellent ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. Based)
Process Method :	Extrusion, coextrusion, sheet extrusion
Uses :	Extruded parts (seals, tubes, profiles, hoses, etc.) for automotive, construction, home appliances, furniture

	Value	Unit	Standard
Physical			
Hardness	85	SHORE A	ISO 868 (3 second)
Density	1,08	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	3,8	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	5	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	13,6	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	630	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	50	N/mm	ISO 34-1 Method B
Aging			
Compression Set (72h/23°C)	31	%	ISO 815
Compression Set (22h/70°C)	54	%	ISO 815

Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair



Ravago Petrokimya Uretim A.S.

ENSOFT SD-141-85A

ENSOFT-S



Sulphuric Acid	Good
----------------	------

Detergent	Good
-----------	------

Drying Condition

Drying Time(hr)	Not required
-----------------	--------------

Drying Temperature(°C)	Not required
------------------------	--------------

Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
----------------------------	-----------

Compression Zone Temperature (°C)	180 - 195
-----------------------------------	-----------

Melting Zone Temperature (°C)	195 - 205
-------------------------------	-----------

Extruder Head Temperature (°C)	200 - 210
--------------------------------	-----------

Die Temperature (°C)	200 - 220
----------------------	-----------

