



RAVATHANE[®]

Technical Data Sheet

Ravathane[®] 210 A95 UV

Description: Thermoplastic polyurethane based on polyether having strong resilience and tear resistance, excellent abrasion resistance, excellent resistance to hydrolysis failure, microbial attack and light.

Application: Injection molding.

Typical Properties

PROPERTIES	TEST METHOD	UNITS	VALUES
Hardness	ISO 868	Shore A	95
Density	ISO 1183-1 A	g/cm ³	1,14
Tensile stress at: -100% elongation	ISO 37	MPa	11
-300% elongation	ISO 37	MPa	20
Tensile strength at break	ISO 37	MPa	50
Elongation at break	ISO 37	%	600
Tear strength	ISO 34-1 B/b	N/mm	130
Abrasion resistance	ISO 4649	mm ³	40

Properties have been tested on injection molded plaques conditioned 24 hours at room temperature before testing.

Application Guideline (Injection Molding)

Nozzle (°C)	Metering (°C)	Compression (°C)	Feed (°C)
200-210	210-220	205-215	195-205

Before processing, the pellets have to be dried at 80-90°C for 2-4 hours. Maximum moisture content should be below 0.02%.