



Preliminary ENSOFT SD30025A-ARY

ENSOFT

Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is produced with food contact compliant raw materials, unfilled, high performance and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery.
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Translucent Good ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. based)
Process Method :	Extrusion, coextrusion, sheet extrusion
Uses :	Extruded parts (seals, tubes, profiles, hoses, etc.) for construction, furniture, home appliances

	Value	Unit	Standard
Physical			
Hardness	25	SHORE A	ISO 868 (3 second)
Density	0,9	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	0,4	Mpa	ISO 37, DIN 53504
300% Modulus	0,9	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	5	Mpa	ISO 37, DIN 53504,ASTM D412
Elongation at Break	>900	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	20	N/mm	ISO 34-1

Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good



Ravago Petrokimya Uretim A.S.



Preliminary ENSOFT SD30025A-ARY

ENSOFT

Detergent	Good
Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Extrusion Condition (°C)

Feed Zone Temperature (°C)	150 - 170
Compression Zone Temperature (°C)	160 - 175
Melting Zone Temperature (°C)	175 - 185
Extruder Head Temperature (°C)	180 - 190
Die Temperature (°C)	180 - 200

Important Notice;

The above results are obtained from the tests conducted in Ravago Petrokimya laboratories on injection molded ISO samples and cannot be used directly to determine end-use or design specification. Datasheet values represent a statistical average of product properties and they may be subject to change as new information becomes available. Customers and other users should make their own independent determination that the product is suitable for the intended use. Ravago Petrokimya accepts no responsibility for results obtained by the application of this information and disclaims all warranties that might arise in connection with this information.