



## ENSOFT SD-151-90A

### ENSOFT-S

<b>Product Description :</b>	This polyolefin based thermoplastic elastomer (SEBS) compound is high mineral filled, completely recyclable and suitable for general purpose applications. ENSOFT® series can be processed with conventional thermoplastics machinery.
<b>Additive Packages :</b>	T / Heat and UV stabilizer /
<b>Key Features :</b>	Excellent ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. based)
<b>Process Method :</b>	Extrusion, coextrusion, sheet extrusion
<b>Uses :</b>	Extruded parts (seals, tubes, profiles, hoses, etc.) for automotive, construction, home appliances, furniture

	Value	Unit	Standard
<b>Physical</b>			
Hardness	90	SHORE A	ISO 868 (3 second )
Density	1,15	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
100% Modulus	4,8	Mpa	ISO 37, DIN 53504
300% Modulus	6,1	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	12,5	Mpa	ISO 37, DIN 53504
Elongation at Break	625	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	70	kN/m	ISO 34-1
<b>Thermal</b>			
Max. Dynamic Service Temperature	90	°C	*
Max. Static Service Temperature	135	°C	*
<b>Environmental Resistance</b>			
Ozone	Excellent		
Water	Excellent		
Alcohol	Excellent		





## ENSOFT SD-151-90A

### ENSOFT-S

---

Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

---

#### Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

---

#### Molding Condition (°C)

1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

---

#### Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

