



ENSOFT SD-641-55D

ENSOFT-S

Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is medium mineral filled, completely recyclable and specifically designed for extrudability at low temperatures. ENSOFT® series can be processed with conventional thermoplastics machinery
Additive Packages :	D / Heat and UV stabilizer and lubricant /
Key Features :	Excellent ozone, UV and weathering resistance Extra smooth, silky surface appearance Rubberlike elasticity in a wide temperature range Ease of processing at lower temperatures Easy colorability with proper MB (PE, PP, etc. Based)
Process Method :	Extrusion, coextrusion, sheet extrusion
Uses :	Extruded parts(seals, tubes, profiles, hoses, etc.) for automotive, construction, home appliances, furniture

	Value	Unit	Standard
Physical			
Hardness	55	SHORE D	ISO 868 (3 second)
Density	1,09	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	13,5	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	13	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	16	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	610	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	100	N/mm	ISO 34-1 Method B

Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair



Ravago Petrokimya Uretim A.S.



ENSOFT SD-641-55D

ENSOFT-S

Sulphuric Acid	Good
----------------	------

Detergent	Good
-----------	------

Drying Condition

Drying Time(hr)	Not required
-----------------	--------------

Drying Temperature(°C)	Not required
------------------------	--------------

Extrusion Condition (°C)

Feed Zone Temperature (°C)	150 - 170
----------------------------	-----------

Compression Zone Temperature (°C)	160 - 175
-----------------------------------	-----------

Melting Zone Temperature (°C)	170 - 180
-------------------------------	-----------

Extruder Head Temperature (°C)	180 - 190
--------------------------------	-----------

Die Temperature (°C)	180 - 200
----------------------	-----------

