

ENSOFT SO-141-20A

ENSOFT-S



Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is medium mineral filled, completely recyclable and suitable for general purpose applications. ENSOFT® series can be processed with conventional thermoplastics machinery
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Excellent ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. Based)
Process Method :	Injection/multi injection molding
Uses :	Industrial applications, automotive, personal care, toys, consumer goods, home&kitchen appliances

	Value	Unit	Standard
Physical			
Hardness	20	SHORE A	ISO 868 (3 second)
Density	1,08	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	0,3	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	0,7	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	2	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	650	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	10	N/mm	ISO 34-1 Method B

Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition



Ravago Petrokimya Uretim A.S.

ENSOFT SO-141-20A

ENSOFT-S



Drying Time(hr)	Not required
-----------------	--------------

Drying Temperature(°C)	Not required
------------------------	--------------

Molding Condition (°C)

1st Zone (hopper)(°C)	150-160
-----------------------	---------

2nd Zone(°C)	160-170
--------------	---------

3rd Zone(°C)	170-180
--------------	---------

Nozzle(°C)	185-190
------------	---------

Melt Temperature(°C)	190-200
----------------------	---------

Mold Temperature(°C)	10-50
----------------------	-------

Max Allowable Melt Temperature(°C)	250 C
------------------------------------	-------

