



ENSOFT SL-584-60A

ENSOFT-S

Product Description :	This polyolefin based flame retardant thermoplastic elastomer (SEBS) compound is dioxine free and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery.
Additive Packages :	F / Heat and UV stabilizer and flame Retardant /
Key Features :	V0 at 1,6 mm according to UL94 (internally tested). Excellent ozone, UV and weathering resistance. Rubberlike elasticity in a wide temperature range. Easy colorability with proper MB (PE, PP, etc. based).
Process Method :	Extrusion, coextrusion, sheet extrusion
Uses :	Extruded parts (seals, tubes, profiles, hoses, etc.) for automotive, transportation, wire&cable, electric&electronics, home appliances

	Value	Unit	Standard
Physical			
Hardness	60	SHORE A	ISO 868 (3 second)
Density	1,32	gr / cm3	ISO 1183 1-A
Brittleness Temperature	-55	°C	ASTM D746
Mechanical			
100% Modulus	2,4	Mpa	ISO 37, DIN 53504
300% Modulus	2,9	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	5,5	Mpa	ISO 37, DIN 53504
Elongation at Break	550	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	38	N/mm	ISO 34-1
Flammability			
Flammability (1,6 mm)	V0	*	UL 94
Thermal			
Max. Dynamic Service Temperature	90	°C	*
Max. Static Service Temperature	135	°C	*

Environmental Resistance



Ravago Petrokimya Uretim A.S.



ENSOFT SL-584-60A

ENSOFT-S

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

