



## Preliminary ENSOFT SL-400-90A

### ENSOFT-S

<b>Product Description :</b>	This polyolefin based thermoplastic elastomer (SEBS) compound is transparent, unfilled and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery
<b>Additive Packages :</b>	T / Heat and UV stabilizer /
<b>Key Features :</b>	Transparent Excellent ozone and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. based).
<b>Process Method :</b>	Extrusion, coextrusion, sheet extrusion
<b>Uses :</b>	Extruded parts (seals, tubes, profiles, hoses, etc.) for construction and furniture

	Value	Unit	Standard
<b>Physical</b>			
Hardness	90	SHORE A	ISO 868 (3 second)
Density	0,9	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
100% Modulus	4,5	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	6,2	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	12,9	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	731	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	72	N/mm	ISO 34-1 Method B

#### Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good



Ravago Petrokimya Uretim A.S.



## Preliminary ENSOFT SL-400-90A

### ENSOFT-S

---

#### Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

---

#### Extrusion Condition (°C)

Feed Zone Temperature (°C)	170 - 190
Compression Zone Temperature (°C)	180 - 195
Melting Zone Temperature (°C)	195 - 205
Extruder Head Temperature (°C)	200 - 210
Die Temperature (°C)	200 - 220

