



ENSOFT SO-300-40D

ENSOFT-S

Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is unfilled, high performance and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Translucent Good ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. based)
Process Method :	Injection/multi injection molding
Uses :	Industrial applications, personal care, toys, consumer goods, home and kitchen appliances

	Value	Unit	Standard
Physical			
Hardness	40	SHORE D	ISO 868 (3 second)
Density	0,9	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	9,5	Mpa	ISO 37, DIN 53504
300% Modulus	10,5	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	11	Mpa	ISO 37, DIN 53504,ASTM D412
Elongation at Break	>500	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	85	N/mm	ISO 34-1

Environmental Resistance

Ozone	Excellent
Water	Excellent



Ravago Petrokimya Uretim A.S.



ENSOFT SO-300-40D

ENSOFT-S

Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Molding Condition (°C)

1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

