



ENSOFIT SO-320-55A

Ravago Manufacturing Turkey - Thermoplastic Elastomer

General Information

Product Description

This polyolefin based thermoplastic elastomer (SEBS) compound is low mineral filled, high performance and completely recyclable. ENSOFIT® series can be processed with conventional thermoplastics machinery

Additive Packages :

T / Heat and UV stabilizer

Key Features :

Excellent ozone, UV and weathering resistance

Rubberlike elasticity in a wide temperature range

Low compression set

Easy colorability with proper MB (PE, PP, etc. based)

Process Method :

Injection/multi injection molding

Uses :

Industrial applications, automotive, consumer goods, home&kitchen appliances

General

Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Filler / Reinforcement	• Mineral		
Additive	• Heat Stabilizer	• UV Stabilizer	
Features	• Chemical Resistant	• High Elasticity	
	• Good Colorability	• Low Compression Set	• UV Resistant
	• Good Weather Resistance	• Ozone Resistant	• UV Stabilized
	• Heat Stabilized	• Recyclable Material	
Uses	• Appliances	• Consumer Applications	
	• Automotive Applications	• Industrial Applications	
Processing Method	• Injection Molding	• Multi Injection Molding	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.980	g/cm ³	ISO 1183/A
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	1.50	MPa	ISO 37
Tensile Stress (300% Strain)	2.10	MPa	ISO 37
Tensile Stress (Break)	7.90	MPa	ISO 37
Tensile Elongation (Break)	780	%	ISO 37
Tear Strength - Across Flow	32.0	kN/m	ISO 34-1
Compression Set			ASTM D395B
23°C, 72 hr	18	%	
70°C, 22 hr	35	%	

ENSOFIT SO-320-55A

Ravago Manufacturing Turkey - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 3 sec)	55		ISO 868
Thermal	Nominal Value	Unit	
Brittleness Temperature	-55.0	°C	
Service Temperature			
Dynamic	90	°C	
Static	110	°C	

Processing Information			
Injection	Nominal Value	Unit	
Hopper Temperature	170 to 180	°C	
Middle Temperature	180 to 190	°C	
Front Temperature	190 to 200	°C	
Nozzle Temperature	200 to 210	°C	
Processing (Melt) Temp	210 to 220	°C	
Mold Temperature	10 to 50	°C	
Injection Notes			
Max Allowable Melt Temperature: 250°C			

Notes

¹ Typical properties: these are not to be construed as specifications.