



ENSOFT SO-300-55A

Ravago Manufacturing Turkey - Thermoplastic Elastomer

General Information

Product Description

This polyolefin based thermoplastic elastomer (SEBS) compound is unfilled, high performance and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery

Additive Packages :

T / Heat and UV stabilizer

Key Features :

Translucent

Excellent ozone, UV and weathering resistance

Rubberlike elasticity in a wide temperature range

Low compression set

Easy colorability with proper MB (PE, PP, etc. based)

Process Method :

Injection/multi injection molding

Uses :

Industrial applications, personal care, toys, consumer goods, home&kitchen appliances

General

Material Status	• Commercial: Active		
Availability	• Europe	• North America	
Additive	• Heat Stabilizer	• UV Stabilizer	
Features	• Chemical Resistant • Good Colorability • Good Weather Resistance • Heat Stabilized	• High Elasticity • Low Compression Set • Ozone Resistant • Recyclable Material	• UV Resistant • UV Stabilized
Uses	• Appliances • Consumer Applications	• Industrial Applications • Personal Care	• Toys
Appearance	• Translucent		
Processing Method	• Injection Molding	• Multi Injection Molding	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	0.900	g/cm ³	ISO 1183/A
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	1.60	MPa	ISO 37
Tensile Stress (300% Strain)	2.30	MPa	ISO 37
Tensile Stress (Break)	7.00	MPa	ISO 37
Tensile Elongation (Break)	> 800	%	ISO 37
Tear Strength - Across Flow	34.0	kN/m	ISO 34-1
Compression Set			ASTM D395B
23°C, 72 hr	16	%	
70°C, 22 hr	36	%	

ENSOFTE SO-300-55A

Ravago Manufacturing Turkey - Thermoplastic Elastomer

Hardness	Nominal Value	Unit	Test Method
Shore Hardness (Shore A, 3 sec)	55		ISO 868
Thermal	Nominal Value	Unit	
Brittleness Temperature	-55.0	°C	
Service Temperature			
Dynamic	90	°C	
Static	110	°C	

Processing Information			
Injection	Nominal Value	Unit	
Hopper Temperature	170 to 180	°C	
Middle Temperature	180 to 190	°C	
Front Temperature	190 to 200	°C	
Nozzle Temperature	200 to 210	°C	
Processing (Melt) Temp	210 to 220	°C	
Mold Temperature	10 to 50	°C	
Injection Notes			
Max Allowable Melt Temperature: 250°C			

Notes

¹ Typical properties: these are not to be construed as specifications.