



## ENSOFT SO-326-60A

### ENSOFT-S

<b>Product Description :</b>	This polyolefin based thermoplastic elastomer (SEBS) compound is low mineral filled, high performance and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery
<b>Additive Packages :</b>	T / Heat and UV stabilizer /
<b>Key Features :</b>	Low fogging and odour Excellent ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range Low compression set Easy colorability with proper MB (PE, PP, etc. based)
<b>Process Method :</b>	Injection/multi injection molding
<b>Uses :</b>	Industrial applications, automotive, consumer goods

	Value	Unit	Standard
<b>Physical</b>			
Hardness	60	SHORE A	ISO 868 (3 second)
Density	0,98	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
100% Modulus	1,8	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	2,8	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	7,9	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	750	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	25	N/mm	ISO 34-1 Method B
<b>Aging</b>			
Change in Elongation (14 days /125°C)	28	%	ISO 188
Compression Set (72h/23°C)	43	%	ISO 815
Compression Set (22h/70°C)	59	%	ISO 815
<b>Thermal</b>			
Fogging (100°C, 16h, post test cond. 4h)	< 2,0	mg	DIN 75201, ISO 6452, SAE J1756





## ENSOFT SO-326-60A

### ENSOFT-S

---

#### Environmental Resistance

Ozone	Excellent
Water	Excellent
Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

---

#### Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

---

#### Molding Condition (°C)

1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

