



ENSOFT SX-141-55A

ENSOFT-S

Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is medium mineral filled, completely recyclable and suitable for general purpose applications. ENSOFT® series can be processed with conventional thermoplastics machinery
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Excellent ozone, UV and weathering resistance Rubberlike elasticity in a wide temperature range Super high flow for difficult injection molding applications Easy colorability with proper MB (PE, PP, etc. based)
Process Method :	Injection/multi injection molding
Uses :	Industrial applications, automotive, personal care, toys, consumer goods, home&kitchen appliances

	Value	Unit	Standard
Physical			
Hardness	55	SHORE A	ISO 868 (3 second)
Density	1,08	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	1,5	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	1,9	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	7,2	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	740	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	19	N/mm	ISO 34-1 Method B
Aging			
Compression Set (72h/23°C)	25	%	ISO 815
Compression Set (22h/70°C)	41	%	ISO 815
Compression Set (22h/100°C)	73	%	ISO 815
Environmental Resistance			
Ozone	Excellent		
Water	Excellent		





ENSOFT SX-141-55A

ENSOFT-S

Alcohol	Excellent
Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Molding Condition (°C)

1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

