



ENSOFT SX-400-65A

ENSOFT-S

Product Description :	This polyolefin based thermoplastic elastomer (SEBS) compound is produced with food contact compliant raw materials, unfilled and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Transparent Ozone and weathering resistance Rubberlike elasticity in a wide temperature range Super high flow for difficult injection molding applications Easy colorability with proper MB (PE, PP, etc. based).
Process Method :	Injection/multi injection molding
Uses :	Industrial applications, personal care, toys, consumer goods

	Value	Unit	Standard
Physical			
Hardness	65	SHORE A	ISO 868 (3 second)
Density	0,9	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	2,4	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	3,7	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	7	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	650	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	33	N/mm	ISO 34-1 Method B
Aging			
Compression Set (72h/23°C)	34	%	ISO 815
Environmental Resistance			
Ozone	Excellent		
Water	Excellent		
Alcohol	Excellent		



Ravago Petrokimya Uretim A.S.



ENSOFT SX-400-65A

ENSOFT-S

Olive Oil	Fair
Sulphuric Acid	Good
Detergent	Good

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Molding Condition (°C)

1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C

