



Sconablend[®] TPE 40 X 114 Natural

Characteristics

thermoplastic elastomer

Sconablend[®] TPE 40 X 114 is a compound for thermoplastic processing with rubber - like properties.

Sconablend[®] TPE 40 X 114 provides a number of outstanding physical properties:

- ◆ high elasticity, flexural and tensile strength
- ◆ low density
- ◆ good flexibility at low temperatures and ageing properties
- ◆ good resistance to ageing (≥ 700 h at 150 °C)
- ◆ easy colouring
- ◆ reuse of in-plant waste without difficulties
- ◆ excellent processing properties

Properties / Application

With its wide range of excellent properties, **Sconablend[®] TPE 40 X 114** can be used for numerous applications e.g. technical goods for the automotive industry, handles for sporting goods and toy parts.

Sconablend[®] TPE 40 X 114 has excellent adhesion to polyolefines, blends and composites based on polyolefines. Therefore it opens interesting possibilities for solutions in the production and processing of hard - soft connections by two component injection-moulding or coextrusion welding, e.g. sealing lips for fan systems, encapsulation of tools and impellers.

Processing

Sconablend[®] TPE 40 X 114 can be processed by injection-moulding and extrusion.

Injection-moulding melt temperatures ranging from **180°C to 250°C** and mould temperatures ranging from **30°C to 50°C** are recommended.

The injection rate should be as high as possible.

The extrusion of **Sconablend[®] TPE 40 X 114** requires melt temperatures between 150°C and 180°C

Sconablend[®] TPE 40 X 114 is not hygroscopic and therefore drying is not necessary if the material is stored properly.

Supply and storage

Sconablend[®] TPE 40 X 114 is supplied in the form of cylindrical granules in **natural tone**. It is delivered in PE bags of 25 kg.

The material should be stored in the original packing in dry rooms at temperatures lower than 35°C and protected from detrimental factors such as water and / or intensive solar radiation.





Sconablend® TPE 40 X 114 Natural

Typical characteristics

Eigenschaften/ Caracteristiques/ Characteristics	Einheit/ Unites/ Units	Norm/ Methodes d' essai/ Test method	Wert/ Valeurs/ Values
Dichte/Dendité/Density	g/cm ³	ISO 1183	1,09 ± 0,03
Härte/Dureté/Hardness	Shore A	ISO 868	42 ± 5
Modul, 100%/Module, 100%/Modulus at 100% - längs/longitudinal/longitudinal - quer/transversal/transverse	N/mm ²	ISO 527	> 0,9 > 0,7
Zugfestigkeit/Résistance en traction au seuil/ Tensile strength at yield - längs/longitudinal/longitudinal - quer/transversal/transverse	N/mm ²	ISO 527	> 4,5 > 7,5
Bruchdehnung/Allongement de rupture/ Strain at break - längs/longitudinal/longitudinal - quer/transversal/transverse	%	ISO 527	> 650 > 770
Druckverformungsrest (22h, 70°C)/Déformation rémanente/Compression set	%	ISO 815	< 35

The information, properties and recommendations in this file are based on the current technical knowledge and past experience. They are provided for general guidance only. All recommendations and suggestions are therefore made without guarantee.

