



## Preliminary ENSOFT TO-630-70A

### ENSOFT-T

<b>Product Description :</b>	This polyolefin based thermoplastic elastomer (SBS) compound is low mineral filled, high performance and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery.
<b>Additive Packages :</b>	T / Heat and UV stabilizer /
<b>Key Features :</b>	Ozone and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. based)
<b>Process Method :</b>	Injection / multi injection molding
<b>Uses :</b>	Industrial applications, house appliances, consumer goods

	Value	Unit	Standard
<b>Physical</b>			
Hardness	70	SHORE A	ISO 868 (3 second)
Density	1,04	gr / cm3	ISO 1183 1-A
<b>Mechanical</b>			
100% Modulus	1,82	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	2,77	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	7,98	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	694	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	27	N/mm	ISO 34-1 Method B
<b>Environmental Resistance</b>			
Water	Excellent		
<b>Drying Condition</b>			
Drying Time(hr)	Not required		
Drying Temperature(°C)	Not required		
<b>Molding Condition (°C)</b>			
1st Zone (hopper)(°C)	150-160		
2nd Zone(°C)	160-170		



Ravago Petrokimya Uretim A.S.



## Preliminary ENSOFT TO-630-70A

### ENSOFT-T

---

3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	230 C

