



ENSOFT TX-160-25A

ENSOFT-T

Product Description :	This polyolefin based thermoplastic elastomer (SBS) compound is high mineral filled, general purpose grade and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery.
Additive Packages :	A / Heat and UV stabilizer and antistatic additive /
Key Features :	Ozone and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. based)
Process Method :	Injection / multi injection molding
Uses :	Industrial applications, house appliances, consumer goods

	Value	Unit	Standard
Physical			
Hardness	25	SHORE A	ISO 868 (3 second)
Density	1,18	gr / cm3	ISO 1183 1-A
Brittleness Point	-40	°C	*
Mechanical			
100% Modulus	0,4	Mpa	ISO 37, DIN 53504
300% Modulus	0,7	Mpa	ISO 37, DIN 53504
Tensile Strength At Break	2,1	Mpa	ISO 37, DIN 53504
Elongation at Break	650	%	ISO 37, DIN 53504
Tear Strength (Perpendicular to flow)	11	kN/m	ISO 34-1
Aging			
Compression Set (72h/23°C)	18	%	ASTM D 395-89-B
Thermal			
Max. Dynamic Service Temperature	70	°C	*
Max. Static Service Temperature	90	°C	*

Environmental Resistance



Ravago Petrokimya



ENSOFT TX-160-25A

ENSOFT-T

Water	Excellent
Drying Condition	
Drying Time(hr)	Not required
Drying Temperature(°C)	Not required
Molding Condition (°C)	
1st Zone (hopper)(°C)	150-160
2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	250 C
