



ENSOFT TO-620-65A

ENSOFT-T

Product Description :	This polyolefin based thermoplastic elastomer (SBS) compound is low mineral filled, high performance and completely recyclable. ENSOFT® series can be processed with conventional thermoplastics machinery.
Additive Packages :	T / Heat and UV stabilizer /
Key Features :	Ozone and weathering resistance Rubberlike elasticity in a wide temperature range Easy colorability with proper MB (PE, PP, etc. based)
Process Method :	Injection / multi injection molding
Uses :	Industrial applications, house appliances, consumer goods

	Value	Unit	Standard
Physical			
Hardness	65	SHORE A	ISO 868 (3 second)
Density	0,99	gr / cm3	ISO 1183 1-A
Mechanical			
100% Modulus	2,2	Mpa	ISO 37(S1,500 mm/min)
300% Modulus	3,2	Mpa	ISO 37(S1,500 mm/min)
Tensile Strength At Break	5	Mpa	ISO 37(S1,500 mm/min)
Elongation at Break	650	%	ISO 37(S1,500 mm/min)
Tear Strength (Perpendicular to flow)	34	N/mm	ISO 34-1 Method B

Environmental Resistance

Water	Excellent
-------	-----------

Drying Condition

Drying Time(hr)	Not required
Drying Temperature(°C)	Not required

Molding Condition (°C)

1st Zone (hopper)(°C)	150-160
-----------------------	---------



Ravago Petrokimya Uretim A.S.



ENSOFT TO-620-65A

ENSOFT-T

2nd Zone(°C)	160-170
3rd Zone(°C)	170-180
Nozzle(°C)	185-190
Melt Temperature(°C)	190-200
Mold Temperature(°C)	10-50
Max Allowable Melt Temperature(°C)	230 C

