

Grilon BS 23

PA6

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Product Texts

Product designation according to ISO 1874:

PA 6, MR, 12-030 N

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	3500 / 1300	MPa	ISO 527-1/-2
Stress at break	70 / -	MPa	ISO 527-1/-2
Strain at break	8 / >50	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	- / 45	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	4 / 20	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	4 / 3	kJ/m ²	ISO 179/1eA

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	222 / -	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	60 / -	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	185 / -	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	70 / -	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	90 / -	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	HB / -	class	IEC 60695-11-10
Thickness tested	0.8 / -	mm	IEC 60695-11-10
Max. usage temperature (long term)	70 - 90	°C	ISO 2578
Max. usage temperature (short term)	180	°C	EMS

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	1E12 / 1E11	Ohm*m	IEC 60093
Surface resistivity	- / 1E12	Ohm	IEC 60093
Electric strength	24 / 22	kV/mm	IEC 60243-1
Comparative tracking index	- / 600	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	9 / -	%	Sim. to ISO 62
Humidity absorption	3 / -	%	Sim. to ISO 62
Density	1140 / -	kg/m ³	ISO 1183

Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	0.8 / -	%	ISO 294-4, 2577
Molding shrinkage (normal)	1.1 / -	%	ISO 294-4, 2577

Characteristics
Processing

Injection Molding

Automotive

Air intake systems, Powertrain and Chassis , Interior

Delivery form

Granules

Electricals & Electronics

Electrical appliances

Regional Availability

 North America, Europe, Asia Pacific, South and Central America,
 Near East/Africa

Industry & Consumer goods

Housewares, Mechanical Engineering, Sports & Leisure



Product Attributes

Improved flowability and demoulding, Nucleated

Burning Behaviour

UL V2

