

Grilamid 2S 25 W 20 X black 9992

PA610-I

EMS-GRIVORY | a unit of EMS-CHEMIE AG

Product Texts

 Product designation according to ISO 1874:
 PA610HIP, EH, 22-007

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	750 / 450	MPa	ISO 527-1/-2
Stress at break	40 / 40	MPa	ISO 527-1/-2
Strain at break	>50 / >50	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy impact strength (-30°C)	N / N	kJ/m ²	ISO 179/1eU
Charpy notched impact strength (+23°C)	N / N	kJ/m ²	ISO 179/1eA
Charpy notched impact strength (-30°C)	15 / 15	kJ/m ²	ISO 179/1eA

Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	50 / 35	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	215 / -	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	50 / -	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	115 / -	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	200 / -	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	150 / -	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	HB / -	class	IEC 60695-11-10
Thickness tested	0.8 / -	mm	IEC 60695-11-10
Max. usage temperature (long term)	110 - 130	°C	ISO 2578
Max. usage temperature (short term)	170	°C	EMS

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	1E9 / 1E10	Ohm*m	IEC 60093
Surface resistivity	- / 1E11	Ohm	IEC 60093
Electric strength	38 / 37	kV/mm	IEC 60243-1
Comparative tracking index	- / 600	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	3 / -	%	Sim. to ISO 62
Humidity absorption	0.5 / -	%	Sim. to ISO 62
Density	1030 / -	kg/m ³	ISO 1183

Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	2.3 / -	%	ISO 294-4, 2577
Molding shrinkage (normal)	1.7 / -	%	ISO 294-4, 2577

Characteristics
Processing

Other Extrusion, Profile Extrusion

Delivery form

Granules

Additives

Plasticizer

Product Attributes

Flexible, High viscosity, Bio based Polyamide

Automotive

Air intake systems, Compressed air systems, Hydraulic systems, Fuel systems



Special Characteristics

High impact or impact modified, Light stabilized or stable to light,
Improved UV resistance (outdoor use)

Regional Availability

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa

Electricals & Electronics

Cables & Tubes

Industry & Consumer goods

Hydraulics & Pneumatics

