

**Grilamid 2S XE 10901 nat**  
 PA610

EMS-GRIVORY | a unit of EMS-CHEMIE AG

**Product Texts**

 Product-nomenclature acc. ISO 1874:  
 PA610+X - GHL, 18-007

Mechanical properties	dry / cond	Unit	Test Standard
Tensile Modulus	<b>700 / 350</b>	MPa	ISO 527-1/-2
Stress at 50% strain	<b>25 / 20</b>	MPa	ISO 527-1/-2
Strain at break	<b>&gt;50 / &gt;50</b>	%	ISO 527-1/-2
Charpy impact strength (+23°C)	<b>N / N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength (-30°C)	<b>N / N</b>	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	<b>110 / N</b>	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength (-30°C)	<b>100 / 110</b>	kJ/m <sup>2</sup>	ISO 179/1eA

Mechanical properties (TPE)	dry / cond	Unit	Test Standard
Ball indentation hardness	<b>40 / 25</b>	MPa	ISO 2039-1

Thermal properties	dry / cond	Unit	Test Standard
Melting temperature (10°C/min)	<b>220 / -</b>	°C	ISO 11357-1/-3
Temp. of deflection under load (1.80 MPa)	<b>40 / -</b>	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	<b>50 / -</b>	°C	ISO 75-1/-2
Coeff. of linear therm. expansion (parallel)	<b>170 / -</b>	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion (normal)	<b>170 / -</b>	E-6/K	ISO 11359-1/-2
Burning Behav. at thickness h	<b>HB / -</b>	class	IEC 60695-11-10
Thickness tested	<b>0.8 / -</b>	mm	IEC 60695-11-10
Max. usage temperature (long term)	<b>90 - 100</b>	°C	ISO 2578
Max. usage temperature (short term)	<b>150</b>	°C	EMS

Electrical properties	dry / cond	Unit	Test Standard
Volume resistivity	<b>1E9 / 1E9</b>	Ohm*m	IEC 60093
Surface resistivity	<b>- / 1E10</b>	Ohm	IEC 60093
Electric strength	<b>38 / 38</b>	kV/mm	IEC 60243-1
Comparative tracking index	<b>- / 600</b>	-	IEC 60112

Other properties	dry / cond	Unit	Test Standard
Water absorption	<b>1.3 / -</b>	%	Sim. to ISO 62
Humidity absorption	<b>0.6 / -</b>	%	Sim. to ISO 62
Density	<b>1010 / -</b>	kg/m <sup>3</sup>	ISO 1183

Rheo/Phys properties	dry / cond	Unit	Test Standard
Molding shrinkage (parallel)	<b>1.0 / -</b>	%	ISO 294-4, 2577
Molding shrinkage (normal)	<b>1.6 / -</b>	%	ISO 294-4, 2577

**Characteristics**
**Processing**

Injection Molding, Other Extrusion

**Product Attributes**

Flexible, Bio based Polyamide

**Delivery form**

Granules

**Automotive**

Compressed air systems, Hydraulic systems

**Special Characteristics**

High impact or impact modified, Improved UV resistance (outdoor

**Electricals & Electronics**

Cables &amp; Tubes



use)

Industry & Consumer goods

Regional Availability

Hydraulics & Pneumatics, Sports & Leisure, Tools & Accessories

North America, Europe, Asia Pacific, South and Central America,  
Near East/Africa

