

ASA Resin ASA 树脂
TOYOLAC™ TA44 X50

FEATURE 特点

High Heat

高耐热

APPLICATION 用途

Building Materials, Automotive Parts

建筑材料, 汽车配件, 一般应用

TECHNICAL DATA SHEET 技术数据表

PROPERTY 性能	TEST METHOD 测试方法	TEST CONDITION 测试条件	UNITS 单位	TOYOLAC™ TA44 X50
Physical Properties 物理性能				
Density 密度	ISO 1183	23 °C	kg/m³	1089
Melt Flow Rate 流动系数	ISO 1133	220 °C / 10 kg	g/10 min	6
Mold Shrinkage 成型收缩率	-	-	-	-
Glass Content 玻纤含量	-	-	-	-
Mechanical Properties 机械性能				
Charpy Impact Strength, Notched Charpy 耐冲击强度, 缺口	ISO 179/1eA	23 °C / 50% RH	kJ/m²	11
Tensile Strength 拉伸强度-降伏点	ISO 527	50 mm / min	MPa	50
Tensile Elongation at Break 拉伸伸长率-断裂点	ISO 527	50 mm / min	%	6
Tensile Modulus 拉伸模数	ISO 527	1 mm / min	MPa	2385
Flexural Strength 弯曲强度	ISO 178	2 mm / min	MPa	76
Flexural Modulus 弯曲模数	ISO 178	2 mm / min	MPa	2350
Thermal Properties 热性能				
Deflection Temperature Under Load 热变形温度	ISO 75	1.8 MPa / 120 °C/hr	°C	90
Appearance 表面				
Glossiness 光泽度	Toray Method	Incident Angle 60°	%	87
Light Transmittance 光线透光率	-	-	-	-
Haze 模糊系数	-	-	-	-
Flammability 燃烧性				
Flammability 燃烧性	-	-	-	-

TORAY PLASTICS (MALAYSIA) SDN BERHAD 东丽塑料大马有限公司

