

Property	Test Condition	Test Method ISO	Units	GF+Mineral filler reinforced
				Toughness, Low gas, Low war page
				LX70T45
				>LCP-(GF+MD)45<
<b>Physical property</b>				
Specific Gravity		ASTM D792	-	1.75
<b>Mechanical property</b>				
Tensile strength		ASTM D638	MPa	130
Tensile elongation at Break		ASTM D638	%	3
Flexural Strength		ASTM D790	MPa	175
Flexural Modulus		ASTM D790	GPa	14.5
Izot impact V-notched		ASTM D256	J/m	60
<b>Heat property</b>				
Heat Deflection Temp High Load	1.82MPa	ASTM D648	°C	250
Flammability		UL94	rank/thickness m mt	V-0(0.38)
Linear Thermal Expansion		ASTM D696	$\times 10^{-5}/K$	1.1~1.9
<b>Molding property</b>				
Mold shrinkage(Machine Direction)	80×80×1mmt	Toray Method	%	0.04
Mold shrinkage(Transverse Direction)	80×80×1mmt	Toray Method	%	0.54

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

COPYRIGHT © TORAY INDUSTRIES,INC

