

Property	Test Condition	Test Method ISO	Units	GF+Mineral filler reinforced	
				Antistatic, Sliding	
				LX70G35C	
				>LCP-(GF+X)35<	
Physical property					
Specific Gravity		ASTM D792	-		1.64
Mechanical property					
Tensile strength		ASTM D638	MPa		130
Tensile elongation at Break		ASTM D638	%		3.5
Flexural Strength		ASTM D790	MPa		160
Flexural Modulus		ASTM D790	GPa		13.5
Izot impact V-notched		ASTM D256	J/m		60
Heat property					
Heat Deflection Temp High Load	1.82MPa	ASTM D648	°C		240
Flammability		UL94	rank/thickness m mt		V-0(0.38)
Linear Thermal Expansion		ASTM D696	$\times 10^{-5}/K$		-
Molding property					
Mold shrinkage(Machine Direction)	80×80×1mmt	Toray Method	%		-
Mold shrinkage(Transverse Direction)	80×80×1mmt	Toray Method	%		-

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

COPYRIGHT © TORAY INDUSTRIES,INC

