

Property	Test Condition	Test Method ISO	Units	Mineral filler reinforced	
				Toughness, Low gas, Low warpage, High flow	
				LX70U30	
				>LCP-MD35<	
Physical property					
Specific Gravity		ASTM D792	-		1.64
Mechanical property					
Tensile strength		ASTM D638	MPa		135
Tensile elongation at Break		ASTM D638	%		3.5
Flexural Strength		ASTM D790	MPa		150
Flexural Modulus		ASTM D790	GPa		14.5
Izot impact V-notched		ASTM D256	J/m		50
Heat property					
Heat Deflection Temp High Load	1.82MPa	ASTM D648	°C		240
Flammability		UL94	rank/thickness mmt		V-0(0.75)
Linear Thermal Expansion		ASTM D696	$\times 10^{-5}/K$		0.7~1.7
Molding property					
Mold shrinkage(Machine Direction)	80×80×1mmt	Toray Method	%		0.05
Mold shrinkage(Transverse Direction)	80×80×1mmt	Toray Method	%		0.21

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

COPYRIGHT © TORAY INDUSTRIES,INC

