

TYPICAL PROPERTIES OF TOYOLAC 834V X01				
Typical Properties	Test Method	Test Conditions	SI Unit	Typical Value
<b>Physical</b>				
Specific Gravity	ASTM D792		-	1.14
Mould Shrinkage	ASTM D955		%	0.4 ~ 0.7
<b>Rheological</b>				
Melt Flow Rate	ISO 1133	200°C / 5 kg	g/10 min	-
	ISO 1133	220°C / 10 kg	g/10 min	32
<b>Mechanical</b>				
Tensile stress at yield	ASTM D638	at 5 mm/min	MPa	42
Tensile strain at break	ASTM D638	at 5 mm/min	%	>5
Flexural Strength	ASTM D790	at 3 mm/min	MPa	65
Flexural Modulus	ASTM D790	at 3 mm/min	MPa	2200
Rockwell Hardness	ASTM D785	R scale	-	103
<b>Impact</b>				
Izod Impact Strength, notched	ASTM D256	12.7 x 62.5 x 12.7 <sup>t</sup> mm (23°C)	J/m	157
Izod Impact Strength, notched	ASTM D256	12.7 x 62.5 x 3.2 <sup>t</sup> mm (23°C)	J/m	226
<b>Thermal</b>				
HDT (Unannealed) 127 x 12.7 x 6.4 <sup>t</sup> mm	ASTM D648	1.82 MPa Loading, 18.56 kg/cm <sup>2</sup>	°C	84
<b>Flammability</b>				
Flammability	UL 94		-	2.0mmV0
				3.0mm 5VA
				-

Toray Plastics Malaysia Sdn.

