

Property	Test Condition	Test Method ISO	Units	Transparent
				Scratch resistant
				910-X01
				>MABS<
<b>Physical property</b>				
Density	23°C	ISO1183	kg/m <sup>3</sup>	1100
Specific Gravity		ASTM D792	-	1.1
<b>Mechanical property</b>				
Tensile strength	23°C	ISO527-1,2	MPa	57
Elongation at Break	23°C	ISO527-1,2	%	13
Flexural Strength	23°C	ISO178	MPa	85
Flexural Modulus	23°C/50% RH	ISO 178	MPa	2630
Charpy Impact Strength (V-notched)	23°C	ISO179	kJ/m <sup>2</sup>	6
Ball Pressure Temp./0.1mm Vicat Softening Temp.			°C	85~90
<b>Heat property</b>				
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	°C	78
Flammability		UL94	rank/thickness m mt	HB
<b>Molding property</b>				
Mold shrinkage	23°C/50% RH	Toray Method	%	0.4-0.6
Melt Flow Rate	220°C/98N	ISO 1133	g/10min	28
<b>Optical property</b>				
Total Light Transmission	23°C/50% RH 3mm thickness	ISO 13468	%	87
Haze	23°C/50% RH 3mm thickness	ISO 14782	%	3

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

COPYRIGHT © TORAY INDUSTRIES,INC

