

Property	Test Condition	Test Method ISO	Units	Transparent
				Scratch resistant (Blueness reinforced)
				910-X15
				>MABS<
Physical property				
Density	23°C	ISO1183	kg/m ³	1100
Specific Gravity		ASTM D792	-	1.1
Mechanical property				
Tensile strength	23°C	ISO527-1,2	MPa	55
Elongation at Break	23°C	ISO527-1,2	%	14
Flexural Strength	23°C	ISO178	MPa	80
Flexural Modulus	23°C/50%RH	ISO 178	MPa	2440
Charpy Impact Strength (V-notched)	23°C	ISO179	kJ/m ²	8.5
Heat property				
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	°C	78
Flammability		UL94	rank/thickness mmt	HB
Molding property				
Mold shrinkage	23°C/50%RH	Toray Method	%	0.4-0.6
Melt Flow Rate	220°C/98N	ISO 1133	g/10min	26
Optical property				
Total Light Transmission	23°C/50%RH 3mm thickness	ISO 13468	%	87
Haze	23°C/50%RH 3mm thickness	ISO 14782	%	2.4

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

COPYRIGHT © TORAY INDUSTRIES,INC

