

Property	Test Condition	Test Method ISO	Units	Alloy	
				ABS/PA Alloy, GF15%	
				SX10G-15	
				>PA6+ABS-GF15<	
Physical property					
Density	23°C	ISO1183	kg/m ³	1190	
Mechanical property					
Tensile strength	23°C	ISO527-1,2	MPa	110	
Elongation at Break	23°C	ISO527-1,2	%	5	
Flexural Strength	23°C	ISO178	MPa	159	
Flexural Modulus	23°C/50%RH	ISO 178	MPa	4550	
Charpy Impact Strength (V-notched)	23°C	ISO179	kJ/m ²	9	
Heat property					
Heat Deflection Temp High Load	1.80MPa	ISO75-1,2	°C	175	
Molding property					
Melt Flow Rate	240°C/98N	ISO 1133	g/10min	23	

These values are typical data for this product under specific test conditions and not intended for use as limiting specifications.

COPYRIGHT © TORAY INDUSTRIES,INC

