

Electrafil® J-1200/CF/40 NAT

Techmer Polymer Modifiers - *Acrylonitrile Butadiene Styrene*

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East • Asia Pacific	• Europe • Latin America	• North America
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.24		ASTM D792
Molding Shrinkage - Flow (0.125 in)	5.0E-4	in/in	ASTM D955
Water Absorption (24 hr)	0.20	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	17.0	psi	ASTM D638
Tensile Elongation (Break)	1.0	%	ASTM D638
Flexural Modulus	2.30E+6	psi	ASTM D790
Flexural Strength	22.0	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.0	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow	1.1E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0	ohms	ASTM D257
Additional Information			
Surface Resistivity, Techmer Test Method: 1 to 10 ohm			

