

TES ABS-1200/10 WT 7355

Techmer Polymer Modifiers - *Acrylonitrile Butadiene Styrene*

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
RoHS Compliance	• RoHS Compliant
Forms	• Pellets

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.10		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.30	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	550000	psi	ASTM D638
Tensile Strength	8000	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	500000	psi	ASTM D790
Flexural Strength	12000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.1	ft·lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	60		ASTM D785

