

**Plaslube® ABS/PBT GF30 BK**

Techmer Polymer Modifiers - *Acrylonitrile Butadiene Styrene + PBT*

**General**

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
<b>Physical</b>			
Density / Specific Gravity	1.45		ASTM D792
Water Absorption (24 hr)	0.12	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength (Break)	20500	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1.20E+6	psi	ASTM D790
Flexural Strength	28000	psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact (73°F, 0.125 in)	1.9	ft·lb/in	ASTM D256
<b>Thermal</b>			
Deflection Temperature Under Load (66 psi, Unannealed)	440	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	407	°F	ASTM D648
<b>Electrical</b>			
Volume Resistivity	1.0E+17	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	520	V/mil	ASTM D149
<b>Flammability</b>			
Flame Rating (0.06 in)	HB		UL 94

