

HiFill® HDPE MM40

Techmer Polymer Modifiers - *High Density Polyethylene*

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Mica, 40% Filler by Weight
Features	• Chemically Coupled
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.29		ASTM D792
Molding Shrinkage - Flow (0.125 in)	4.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.050	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	4800	psi	ASTM D638
Tensile Elongation (Break)	5.0	%	ASTM D638
Flexural Modulus	750000	psi	ASTM D790
Flexural Strength	6200	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.6	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	112		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	290	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	240	°F	ASTM D648
CLTE - Flow	1.9E-5	in/in/°F	ASTM D696

