

HiFill® HDPE TM30

Techmer Polymer Modifiers - High Density Polyethylene

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Talc, 30% Filler by Weight
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.20		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.015	in/in	ASTM D955
Water Absorption (24 hr)	0.025	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	4400	psi	ASTM D638
Tensile Elongation (Break)	12	%	ASTM D638
Flexural Modulus	200000	psi	ASTM D790
Flexural Strength	65000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	0.70	ft-lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	8.0	ft-lb/in	ASTM D4812
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	70		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	210	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	150	°F	ASTM D648
Melting Temperature	275	°F	
CLTE - Flow	4.5E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	500	V/mil	ASTM D149

