

## Electrafil® J-71/CF/40/EG

Techmer Polymer Modifiers - *Polyamide 6 Alloy*

### General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Carbon Fiber, 40% Filler by Weight
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

### ASTM & ISO Properties <sup>1</sup>

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.30		ASTM D792
Molding Shrinkage - Flow (0.125 in)	5.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.80	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength (Break, 73°F)	28000	psi	ASTM D638
Flexural Modulus (73°F)	3.25E+6	psi	ASTM D790
Flexural Strength (Break, 73°F)	38000	psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact (73°F, 0.125 in)	1.6	ft-lb/in	ASTM D256
<b>Thermal</b>			
Deflection Temperature Under Load (264 psi, Unannealed)	405	°F	ASTM D648

### Processing Information

	Nominal Value	Unit
<b>Injection</b>		
Drying Temperature	220	°F
Drying Time	2.0	hr
Suggested Max Moisture	0.20	%
Rear Temperature	485 to 520	°F
Middle Temperature	500 to 530	°F
Front Temperature	490 to 520	°F
Nozzle Temperature	490 to 520	°F
Processing (Melt) Temp	485 to 530	°F
Mold Temperature	130 to 180	°F
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 50.0	psi

