

**HiFill® J-7/33 BK**

Techmer Polymer Modifiers - *Polyamide 6*

**Product Description**

PNM93899

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Features	• Heat Stabilized	• Impact Modified	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.34		ASTM D792
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Strength	17000	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1.02E+6	psi	ASTM D790
Flexural Strength	34000	psi	ASTM D790
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact	3.9	ft·lb/in	ASTM D256

