

TES J-7/33/V0 BK

Techmer Polymer Modifiers - Polyamide 6

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

ASTM & ISO Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.35		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength	22000	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	1.20E+6	psi	ASTM D790
Flexural Strength	34000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	3.9	ft-lb/in	ASTM D256
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.13 in)	V-0		UL 94

