

Plaslube® PA4/6 CF30 TL10

Techmer Polymer Modifiers - *Polyamide 46*

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Carbon Fiber, 30% Filler by Weight
Additive	• PTFE Lubricant: 10%
Features	• Lubricated
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.39		ASTM D792
Molding Shrinkage - Flow (0.125 in)	1.0E-3 to 3.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.125 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	2.0	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	28000	psi	ASTM D638
Tensile Elongation (Break)	2.6	%	ASTM D638
Flexural Modulus	2.60E+6	psi	ASTM D790
Flexural Strength	42000	psi	ASTM D790
Coefficient of Friction			ASTM D1894
vs. Steel - Dynamic	0.15		
vs. Steel - Static	0.16		
Wear Factor	15	10 ⁻⁴ -10 in ³ ·min/ft·lb·hr	ASTM D3702
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.4	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	560	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	545	°F	ASTM D648
Melting Temperature	563	°F	
CLTE - Flow	1.5E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	10	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value	Unit	Test Method
TPCI #	8661150		

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	185	°F
Drying Time	4.0 to 8.0	hr
Rear Temperature	540 to 600	°F
Middle Temperature	540 to 600	°F
Front Temperature	540 to 600	°F
Processing (Melt) Temp	475 to 600	°F
Mold Temperature	190 to 260	°F
Back Pressure	0.00 to 50.0	psi



