

## Plaslube® PA4/6 GF30 TL15

Techmer Polymer Modifiers - Polyamide 46

### General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Heat Stabilizer • PTFE Lubricant
Features	• Heat Stabilized • Lubricated
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

### Properties <sup>1</sup>

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.51		ASTM D792
Molding Shrinkage - Flow (0.125 in)	6.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	1.5	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength (Break)	26000	psi	ASTM D638
Tensile Elongation (Break)	3.2	%	ASTM D638
Flexural Modulus	1.40E+6	psi	ASTM D790
Flexural Strength	39000	psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact (73°F, 0.125 in)	2.0	ft·lb/in	ASTM D256
<b>Thermal</b>			
Deflection Temperature Under Load (264 psi, Unannealed)	530	°F	ASTM D648
CLTE - Flow	1.0E-5	in/in/°F	ASTM D696
<b>Electrical</b>			
Volume Resistivity	1.0E+14	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	600	V/mil	ASTM D149
<b>Flammability</b>			
Flame Rating (0.06 in)	HB		UL 94

### Processing Information

	Nominal Value	Unit
<b>Injection</b>		
Drying Temperature	185	°F
Drying Time	4.0 to 8.0	hr
Rear Temperature	540 to 600	°F
Middle Temperature	540 to 600	°F
Front Temperature	540 to 600	°F
Processing (Melt) Temp	475 to 600	°F
Mold Temperature	190 to 260	°F
Back Pressure	0.00 to 50.0	psi
Screw Speed	40 to 80	rpm

