

Electrafil® PA6/6 CF40 BK

Techmer Polymer Modifiers - Polyamide 66

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Carbon Fiber, 40% Filler by Weight
Features	• Antistatic • Electrically Conductive
Uses	• Automotive Electronics • Business Equipment • Packaging • Bushings • Conveyor Parts
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.33		ASTM D792
Molding Shrinkage - Flow	1.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.60	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus (73°F)	4.10E+6	psi	ASTM D638
Tensile Strength (73°F)	40000	psi	ASTM D638
Tensile Elongation (Break, 73°F)	1.8	%	ASTM D638
Flexural Modulus (73°F)	3.40E+6	psi	ASTM D790
Flexural Strength (73°F)	59000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.8	ft-lb/in	ASTM D256
Unnotched Izod Impact (73°F, 0.125 in)	15	ft-lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	505	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	495	°F	ASTM D648
CLTE - Flow	8.0E-6	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	55	ohms	ASTM D257
Volume Resistivity	5.5	ohms·cm	ASTM D257
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

Additional Information

Surface Resistivity, ASTM D4496: 10-100 ohms
Volume Resistivity, ASTM C611: 1-10 ohm-cm
Shielding Effectiveness, ES7-83, 1GHz: 30-40 dB

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	530 to 550	°F
Middle Temperature	550 to 570	°F
Front Temperature	540 to 560	°F



Nozzle Temperature	540 to 550 °F
Processing (Melt) Temp	540 to 580 °F
Mold Temperature	175 to 220 °F
Injection Rate	Slow-Moderate
Back Pressure	0.00 to 50.0 psi
Injection Notes	
Screw Speed: Slow	
Recommendations for Molding and Tool Conditions: Well vented mold	
Moisture Content, as received: Product is packaged at 0.2% or less.	

