

Electrafil® PA6/6 GF13 SS10 BK

Techmer Polymer Modifiers - Polyamide 66

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 13% Filler by Weight • Stainless Steel Fiber, 10% Filler by Weight
Features	• Electromagnetic Shielding (EMI)
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.27		ASTM D792
Molding Shrinkage - Flow (0.125 in)	6.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.60	%	ASTM D570
Mechanical			
Tensile Strength (Break)	14000	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Flexural Modulus	790000	psi	ASTM D790
Flexural Strength	21500	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	1.0	ft-lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	9.0	ft-lb/in	ASTM D4812
Thermal			
Deflection Temperature Under Load (264 psi, Unannealed)	480	°F	ASTM D648
Electrical			
Surface Resistivity	1.0E+4	ohms	ASTM D257
Volume Resistivity	1.0E+4	ohms·cm	ASTM D257
EMI Attenuation	40	dB	ASTM D4935
Static Decay	< 0.1	sec	FTMS 101B
Flammability			
Flame Rating (0.06 in)	HB		UL 94

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	180	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	540 to 560	°F
Middle Temperature	550 to 570	°F
Front Temperature	530 to 550	°F
Nozzle Temperature	520 to 580	°F
Processing (Melt) Temp	540 to 580	°F
Mold Temperature	175 to 220	°F
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 50.0	psi

Injection Notes

Screw Speed: Slow
Recommendations for Molding and Tool Conditions: Well vented mold



Moisture Content, as received: Product is packaged at 0.2% or less.

