

HiFill FR® PA6/6 GF25 FR BK

Techmer Polymer Modifiers - Polyamide 66

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant
Appearance	• Black
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.57		ASTM D792
Molding Shrinkage - Flow (0.125 in)	5.0E-3 to 7.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.35E+6	psi	ASTM D638
Tensile Strength (Yield)	21500	psi	ASTM D638
Tensile Strength (Break)	21500	psi	ASTM D638
Tensile Elongation (Break)	2.5	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.0	ft·lb/in	ASTM D256
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.06 in		V-0	
0.12 in		V-0	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	2.0 to 3.0	hr
Rear Temperature	490 to 530	°F
Middle Temperature	500 to 540	°F
Front Temperature	510 to 550	°F
Nozzle Temperature	520 to 555	°F
Processing (Melt) Temp	500 to 555	°F
Mold Temperature	125 to 200	°F
Injection Rate	Slow-Moderate	
Back Pressure	25.0 to 75.0	psi
Screw Speed	Slow	

