

Plaslube® PA6/6,6 L N

Techmer Polymer Modifiers - *Polyamide 66/6 Copolymer*

General

Material Status	• Commercial: Active
Availability	• North America
Additive	• Lubricant • Nucleating Agent
Features	• Copolymer • Lubricated • Fast Molding Cycle • Nucleated
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.12		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.014	in/in	ASTM D955
Water Absorption (24 hr)	1.3	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	11000	psi	ASTM D638
Tensile Elongation (Yield)	90	%	ASTM D638
Flexural Modulus	410000	psi	ASTM D790
Flexural Strength	14000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.5	ft-lb/in	ASTM D256
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	352	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	170	°F	ASTM D648
CLTE - Flow	5.1E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	460	V/mil	ASTM D149
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

