

**Plaslube® PA6/6,6 IM 6040 BK MB**

Techmer Polymer Modifiers - *Polyamide 66/6 Copolymer*

**General**

Material Status	• Commercial: Active
Availability	• North America
Additive	• Heat Stabilizer • Impact Modifier • Lubricant
Features	• Copolymer • Heat Stabilized • Impact Modified • Lubricated
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

**Properties <sup>1</sup>**

	Nominal Value	Unit	Test Method
<b>Physical</b>			
Density / Specific Gravity	1.11		ASTM D792
Molding Shrinkage - Flow	0.013	in/in	ASTM D955
Water Absorption (24 hr)	1.5	%	ASTM D570
<b>Mechanical</b>			
Tensile Strength (Yield)	8000	psi	ASTM D638
Tensile Elongation (Break)	100	%	ASTM D638
Flexural Modulus	250000	psi	ASTM D790
Flexural Strength (Yield)	12000	psi	ASTM D790
<b>Impact</b>			
Notched Izod Impact (0.125 in)	7.0	ft·lb/in	ASTM D256
<b>Hardness</b>			
Rockwell Hardness (R-Scale)	119		ASTM D785
<b>Thermal</b>			
Deflection Temperature Under Load (66 psi, Unannealed)	345	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	150	°F	ASTM D648
CLTE - Flow	5.3E-5	in/in/°F	ASTM D696
<b>Electrical</b>			
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength (Method A (Short-Time))	460	V/mil	ASTM D149
<b>Flammability</b>			
Flame Rating	HB		UL 94

