

Plaslube® PA6/12 GF30 TS15 BK

Techmer Polymer Modifiers - Polyamide 612

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Lubricant
Features	• Lubricated
Appearance	• Black
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.41		ASTM D792
Molding Shrinkage - Flow (0.125 in)	4.0E-3 to 6.0E-3	in/in	ASTM D955
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.32E+6	psi	ASTM D638
Tensile Strength (Yield)	18000	psi	ASTM D638
Tensile Strength (Break)	17500	psi	ASTM D638
Tensile Elongation (Break)	3.0	%	ASTM D638
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.8	ft·lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	180	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	510 to 540	°F
Middle Temperature	520 to 550	°F
Front Temperature	530 to 560	°F
Nozzle Temperature	525 to 555	°F
Processing (Melt) Temp	510 to 555	°F
Mold Temperature	125 to 200	°F
Injection Rate	Slow	
Back Pressure	25.0 to 75.0	psi
Screw Speed	Slow-Moderate	

