

**TES J-71/30/V0/ND BK2791**

Techmer Polymer Modifiers - *Polyamide + SAN*

**General**

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
RoHS Compliance	• RoHS Compliant		
Forms	• Pellets		

**Properties <sup>1</sup>**

<b>Physical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Density / Specific Gravity	1.56		ASTM D792
Water Absorption (24 hr)	0.75	%	ASTM D570
<b>Mechanical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Tensile Strength	18100	psi	ASTM D638
Tensile Elongation (Break)	1.5	%	ASTM D638
Flexural Modulus	1.38E+6	psi	ASTM D790
Flexural Strength	26100	psi	ASTM D790
<b>Impact</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Notched Izod Impact	3.5	ft·lb/in	ASTM D256
<b>Flammability</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Flame Rating (0.13 in)	V-0		UL 94

