

Electrafil® PC-50/EC/VO BK223

Techmer Polymer Modifiers - Polycarbonate

General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	
Additive	• Carbon Black	• Flame Retardant	
Features	• Antistatic	• Electrically Conductive	• Flame Retardant
Uses	• Automotive Electronics	• Business Equipment	• Packaging
	• Bushings	• Conveyor Parts	
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Forms	• Pellets		
Processing Method	• Injection Molding		

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.31		ASTM D792
Molding Shrinkage - Flow (0.125 in)	5.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.15	%	ASTM D570
Mechanical			
Tensile Strength (73°F)	8100	psi	ASTM D638
Flexural Modulus (73°F)	400000	psi	ASTM D790
Flexural Strength (73°F)	12200	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.125 in)	1.0	ft-lb/in	ASTM D256
Thermal			
Deflection Temperature Under Load (264 psi, Unannealed)	260	°F	ASTM D648
Electrical			
Surface Resistivity	5.0E+5	ohms	ASTM D257
Flammability			
Flame Rating (0.06 in)	V-0		UL 94
Additional Information			
Surface Resistivity, ASTM D4496: 1E3-1E6 ohms			

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	250	°F
Drying Time	4.0	hr
Suggested Max Moisture	0.050	%
Rear Temperature	550 to 580	°F
Middle Temperature	560 to 600	°F
Front Temperature	560 to 620	°F
Nozzle Temperature	560 to 610	°F
Processing (Melt) Temp	580 to 620	°F
Mold Temperature	180 to 250	°F
Injection Rate	Moderate	
Back Pressure	50.0 to 100	psi

Injection Notes

Screw Speed: Medium
Recommendations for Molding and Tool Conditions: Well vented mold



Moisture Content, as received: Product is packaged at 0.2% or less.

