

Plaslube® PC-50/TF/13/SI/2 BK3

Techmer Polymer Modifiers - Polycarbonate

General

Material Status	• Commercial: Active
Availability	• North America
Appearance	• Black
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.26	g/cm ³	
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	13	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	7300	psi	ASTM D638
Tensile Stress (Yield)	6890	psi	ISO 527-2
Tensile Elongation (Break)	23	%	ASTM D638
Tensile Strain (Break)	19	%	ISO 527-2
Flexural Modulus	325000	psi	ASTM D790
Flexural Modulus	331000	psi	ISO 178
Flexural Strength	11400	psi	ASTM D790
Flexural Stress	11300	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	4.0	ft·lb/in	ASTM D256
Notched Izod Impact Strength (0.125 in)	11	ft·lb/in ²	ISO 180
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	250	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-2		UL 94

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	250	°F
Drying Time	3.0 to 4.0	hr
Rear Temperature	500 to 540	°F
Middle Temperature	510 to 550	°F
Front Temperature	520 to 560	°F
Nozzle Temperature	530 to 570	°F
Processing (Melt) Temp	510 to 565	°F
Mold Temperature	125 to 200	°F
Injection Rate	Slow-Moderate	
Back Pressure	0.00 to 50.0	psi
Screw Speed	Slow	

