

TES J-50/20

Techmer Polymer Modifiers - Polycarbonate

General

Material Status	• Commercial: Active
Availability	• Africa & Middle East • Europe • North America • Asia Pacific • Latin America
Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Features	• Creep Resistant • Good Dimensional Stability • High Strength • Fatigue Resistant • High Heat Resistance
RoHS Compliance	• RoHS Compliant
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

	Nominal Value	Unit	Test Method
Physical			
Density / Specific Gravity	1.35		ASTM D792
Molding Shrinkage - Flow (0.125 in)	3.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical			
Tensile Modulus (73°F)	900000	psi	ASTM D638
Tensile Strength (Break, 73°F)	16000	psi	ASTM D638
Tensile Elongation (Break, 73°F)	3.0	%	ASTM D638
Flexural Modulus (73°F)	800000	psi	ASTM D790
Flexural Strength (Break, 73°F)	22000	psi	ASTM D790
Impact			
Notched Izod Impact (73°F, 0.250 in)	2.5	ft-lb/in	ASTM D256
Hardness			
Rockwell Hardness (M-Scale)	80		ASTM D785
Thermal			
Deflection Temperature Under Load (66 psi, Unannealed)	305	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Unannealed)	290	°F	ASTM D648
RTI Elec			UL 746B
0.06 in	167	°F	
0.12 in	167	°F	
RTI Imp			UL 746B
0.06 in	167	°F	
0.12 in	167	°F	
RTI Str			UL 746B
0.06 in	167	°F	
0.12 in	167	°F	
Flammability			
Flame Rating			UL 94
0.06 in	V-2		
0.12 in	V-0		

Processing Information

	Nominal Value	Unit
Injection		
Drying Temperature	250	°F
Drying Time	2.0 to 4.0	hr
Suggested Max Moisture	0.10	%
Rear Temperature	570 to 600	°F



Middle Temperature	590 to 650 °F
Front Temperature	600 to 630 °F
Nozzle Temperature	590 to 630 °F
Processing (Melt) Temp	580 to 625 °F
Mold Temperature	160 to 190 °F

