

Electrafil® PC/ABS 03009

Techmer Polymer Modifiers - Polycarbonate + ABS

General

Material Status	• Commercial: Active
Availability	• North America
Filler / Reinforcement	• Filler
Features	• Statically Conductive
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.21		ASTM D792
Molding Shrinkage - Flow (0.125 in)	5.0E-3	in/in	ASTM D955
Water Absorption (24 hr)	0.10	%	ASTM D570
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	8100	psi	ASTM D638
Tensile Elongation (Yield)	7.0	%	ASTM D638
Flexural Modulus	440000	psi	ASTM D790
Flexural Strength	12900	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F, 0.125 in)	1.2	ft·lb/in	ASTM D256
Unnotched Izod Impact (0.125 in)	11	ft·lb/in	ASTM D4812
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (264 psi, Unannealed)	210	°F	ASTM D648
CLTE - Flow	2.2E-5	in/in/°F	ASTM D696
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0 to 1.0E+2	ohms	ASTM D257
Volume Resistivity	1.0 to 1.0E+2	ohms·cm	ASTM D257
Shielding Effectiveness	50	dB	ASTM D4935
Static Decay	< 0.1	sec	MIL PRF-81705D
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	HB		UL 94

